

CERTIFICATE OF ANALYSIS

Zinc alloy ZK series

The assigned values¹ and uncertainties² in % w/w

No. Element	ZK1		ZK2		ZK3		ZK4		ZK5	
Al	11.789	±0.073	10.572	±0.073	9.767	±0.039	8.371	±0.046	6.476	±0.032
Cu	1.538	±0.059	3.119	±0.088	3.996	±0.046	5.487	±0.063	6.663	±0.054
Pb	0.0031	±0.0004	0.0121	±0.0018	0.0226	±0.0019	0.0334	±0.0023	0.0507	±0.0018
Cd	0.0021	±0.0006	0.0031	±0.0004	0.0071	±0.0004	0.0121	±0.0006	0.0207	±0.0011
Sn	0.00085	±0.00016	0.0015	±0.0003	0.00267	±0.00037	0.00491	±0.00053	0.0065	±0.0003
Mg	0.0009	±0.0003	0.0040	±0.0004	0.0307	±0.0036	0.0640	±0.0034	0.0410	±0.0038
Bi	0.200	±0.020	0.169	±0.014	0.102	±0.007	0.0188	±0.0023	0.0020	±0.0004
Sb	0.127	±0.016	0.102	±0.012	0.0674	±0.0055	0.0121	±0.0018	0.0025	±0.0005
Mn	-		0.0137	±0.0012	-		-		0.589	±0.033
Zn	the rest		the rest		the rest		the rest		the rest	

¹ Unweighted mean value of the means of accepted sets of data, each set being obtained in a different laboratory and/or with a different method of determination.

Prof. Zbigniew Śmieszek Director of the Institute

2 June 27

Certified on November 2015

· Pb

² The certified uncertainty is the expanded uncertainty with a coverage factor k=2, corresponding to a level of confidence of about 95 %.



Description of the material:

The certified reference materials are available in the form of discs (40 mm diameter and ~25 mm height).

Analytical methods applied:

Pb, Cd, Sn, Mg, Bi, Sb, Mn – Inductively coupled plasma optical emission spectrometry (ICP OES), Flame atomic absorption spectrometry (FAAS)

Al – Inductively coupled plasma optical emission spectrometry (ICP OES),
Flame atomic absorption spectrometry (FAAS),
Complexometric method

Cu – Inductively coupled plasma optical emission spectrometry (ICP OES),
Flame atomic absorption spectrometry (FAAS),
Iodometric method

Sn – Inductively coupled plasma optical emission spectrometry (ICP OES),
Flame atomic absorption spectrometry (FAAS),
Spectrophotometric method

Participants:

Institute of Non-Ferrous Metals, Analytical Chemistry Department, Gliwice, Poland

- Optical Emission Spectrometry Laboratory
- Atomic Absorption Spectrometry Laboratory
- Classical Analytical Methods Laboratory

Zakłady Górniczo – Hutnicze "Bolesław" S.A., Bukowno, Poland

Intended use:

The CRM is intended for establishing or checking the calibration of optical emission and X-ray spectrometers for analysis of samples of similar matrix composition (for micro-analysis is not verified).

Instructions for use:

Before every use, the surface of CRM must be prepared by milling or turning on a lathe. Samples should be prepared in the same way as the CRM.

Brief description of the production and certification process:

The CRM_s – ZK were made by melting of all components in the inductive, of crucible furnace and by casting into special moulds protecting elimination of segregation of the components during solidification. Homogeneity testing were made taking into account over 50% of the material produced. Investigations were carried out using atomic emission spectrometry method with low voltage spark. Homogeneity was estimated statistically with application of the test F.

The set consists of 5 certified reference materials in form of discs 40 mm in diameter and ~25 mm height.

The certification of ZK series is valid indefinitely, within the measurement uncertainties specified, provided the CRM is handled in accordance with the instructions given in this certificate.

Phone: +48 32 238 04 68 Fax: +48 32 231 69 33 e-mail: crm@imn.gliwice.pl www.imn.gliwice.pl

e Pb